

05/19/00

05-22-00



Please type a plus sign (+) inside this box — +

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Approved for use through 09/30/2000 OMB 0651-0042
Patent and Trademark Office U.S. DEPARTMENT OF COMMERCE

UTILITY PATENT APPLICATION TRANSMITTAL

Attorney Docket No.: Mo-5519/LeA 33,773

First Inventor or Application Identifier: Winfried Jeske et al

Title: DIENE RUBBER COMPOUNDS FOR IMPROVED ...

(Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))

Express Mail Label No.: EK243943585US

APPLICATION ELEMENTS

See MPEP chapter 600 concerning utility patent application contents.

1. ☒ Fee Transmittal Form (e.g., PTO/SB/17)
(Submit an original and a duplicate for fee processing)
2. ☒ Specification (Total Pages: 21)
(preferred arrangement set forth below)
 - Descriptive title of the invention
 - Cross References to Related Applications
 - Statement Regarding Fed sponsored R & D
 - Reference to Microfiche Appendix
 - Background of the invention
 - Brief Summary of the invention
 - Brief Description of the Drawings (if filed)
 - Detailed Description
 - Claim(s)
 - Abstract of the Disclosure
3. ☐ Drawing(s) (35 U.S.C. 113) (Total Sheets:)
4. Oath or Declaration (Total Pages: 2)
 - a. ☒ Newly executed (original or copy)
 - b. ☐ Copy from a prior application (37 C.F.R. § 1.63(d))
(for continuation/divisional with Box 16 completed)
 - i. ☐ DELETION OF INVENTOR(S)
Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).

* NOTE FOR ITEMS 1 & 13: IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.37), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C.F.R. § 1.38).

ADDRESS TO:

Assistant Commissioner for Patents
Box Patent Application
Washington, DC 20231

5. ☐ Microfiche Computer Program (Appendix)
6. Nucleotide and/or Amino Acid Sequence Submission
(if applicable, all necessary)
 - a. ☐ Computer Readable Copy
 - b. ☐ Paper Copy (identical to computer copy)
 - c. ☐ Statement verifying identity of above copies

ACCOMPANYING APPLICATION PARTS

7. ☒ Assignment Papers (cover sheet & document(s))
8. ☐ 37 C.F.R. § 3.73(b) Statement of Power of Attorney
(when there is an assignee)
9. ☐ English Translation Document (if applicable)
10. ☒ Information Disclosure Statement (IDS) PTO-1449 ☒ Copies of IDS Citations
11. ☐ Preliminary Amendment
12. ☒ Return Receipt Postcard (MPEP 503)
(Should be specifically itemized)
13. ☐ Small Entity Statement filed in prior application.
Statement(s) Status still proper and desired
(PTO/SB/09-12)
14. ☐ Certified Copy of Priority Document(s)
(if foreign priority is claimed)
15. ☐ Other:

16. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No.:

Prior application information: Examiner

Group / Art Unit:

For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 4b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.

17. CORRESPONDENCE ADDRESS

☐ Customer Number or Bar Code Label

(Insert Customer No. or Attach bar code label here)

or ☒ Correspondence address below

Name	Bayer Corporation		
	Patent Department		
Address	100 Bayer Road		
City	Pittsburgh	State	PA
Country	USA	Telephone	(412) 777-2349
		Zip Code	15205-9741
		Fax	(412) 777-5449

Name (Print/Type): Noland J. Cheung

Registration No. (Attorney/Agent):

39,138

Signature

Date: 5/19/2000

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231.

DIENE RUBBER COMPOUNDS FOR IMPROVED RUBBER MOLDINGS

FIELD OF THE INVENTION

5

This invention relates to vulcanizable diene rubber compounds which exhibit a high capacity for the addition of sulfur to be varied while processing safety is maintained, for the production of improved rubber moldings, particularly tire components.

10

BACKGROUND OF THE INVENTION

15

Due to the dynamic stresses on a tire, tire components require good thermal and mechanical stability in order to ensure good durability of the tire. With regard to mechanical stability, a high modulus and a high resistance to tear propagation, in particular, are desirable at a given hardness of the vulcanized material.

20

The economics of the use of tires, particularly truck tires, is to a major extent determined by the total number of possible remolds of the tire tread. Repeated remolding of the tire tread is only possible, however, to the extent which is permitted by the stressed carcass of the tire.

α,ω -bis(N,N'-diethylthiocarbamoyldithio)-alkanes and 1,2-bis(N,N'-dibenzylthiocarbamoyldithio)-ethane are known from Patent Applications EP 385 072, EP 385 073, EP 432 405 and EP 432 417 as crosslinking agents for diene rubber for the production of tire treads and tire sidewalls. A common feature of diethylamine derivatives is that they can release diethylamine during the vulcanization of the rubber compound. Diethylamine can form diethylnitrosamine, which is carcinogenic to humans. 1,2-bis-(N,N'-dibenzylthiocarbamoyldithio)-ethane is not, in fact, capable of forming dibenzylnitrosamine, which is carcinogenic to humans (see Druckrey et al., Z. Krebsforschung 69 (1967) 103), but based on the teaching of DE 22 56 511 the possibility cannot be ruled out for this compound, with its 1,2-dithioethanediyl

"Express Mail" mailing label number EK243943585US

Date of Deposit May 19, 2000

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant Commissioner of Patents and Trademarks, Washington, D.C. 20231

Donna J. Veatch

(Name of person mailing paper or fee)

Donna J. Veatch

(Signature of person mailing paper or fee)

radical, resulting in malodorous vulcanized materials (see page 17, paragraph 2), whereas α,ω -dithioalkanediyl radicals which comprise more than 4 carbon atoms result in vulcanized materials which result in no problems as with respect to odor.

5 In the aforementioned European Patent Applications, the crosslinking agents were used without sulfur additives. It is mentioned that the additional use of sulfur generally results in no advantages, since the reversion behavior of the vulcanized materials deteriorates.

10 EP 530 590 discloses a method of producing vulcanized diene rubber materials with a crosslinking agent system consisting of 1 to 4.5 parts by weight of 1,2-bis(N,N'-dibenzylthiocarbamoyldithio)-ethane or of 1,6-bis(N,N'-dibenzylthiocarbamoyldithio)-hexane, 0.05 to 0.3 parts by weight sulfur, and selected amounts of vulcanization accelerators. The particular teaching of the aforementioned patent is that the
15 amount of crosslinking agent used can be reduced (economic aspects) by the use of very small amounts of sulfur, and that elastomers which exhibit a resistance to aging and reversion which was unattainable can be obtained with the avoidance of bloom phenomena and after relatively short times of vulcanization (page 7, lines 25 to 27). Vehicle tires and engine mountings are cited as examples of the use of vulcanized
20 materials such as these.

Furthermore, DE 22 56 511 contains a very general discussion of the use of compounds of general formula A - S - S - R - S - S - A' for the vulcanization of rubbers, wherein R constitutes almost any divalent organic radical, and A and A'
25 constitute a very large number of accelerator radicals, which also include N-substituted thiocarbamoyl radicals amongst others. The crosslinking agents can be used on their own or can also be used in combination with sulfur and vulcanization accelerators. The addition of elemental sulfur preferably falls within the range from 0.5 to 1.5 parts by weight sulfur with respect to 100 parts by weight rubber. Page 32,
30 paragraph 2 contains the teaching that the crosslinking agents of the invention, in

combination with amounts of sulfur greater than 1.5 parts by weight, result in a decrease in the level of processing safety of these rubber compounds.

5 One measure of the level of processing safety is the Mooney scorch time. A short Mooney scorch time signifies a low level of processing safety, whereas a long Mooney scorch time signifies a high level of processing safety. A high level of processing safety of rubber compounds is very desirable, because the addition of vulcanization retarders can thereby be dispensed with.

10 It is shown in DE 22 56 511, using master batch A (an NR compound), that the rubber compound according to Example 7 of Table VII, which comprises 1.0 parts by weight 1,2-bis-N,N'-dimethylthio-carbamoyldithio)-ethane and 1.7 parts by weight sulfur, has a Mooney scorch time ($t_5/121^\circ\text{C}$) of only 25.7 minutes. Compared with this, the compound according to Example 1 of Table III (control example), which
15 comprises 2.0 parts by weight sulfur and 0.5 parts by weight Santocure NS (benzothiazyl-2-tert.-butylsulphenamide, TBBS) as an accelerator, has a corresponding Mooney scorch time of 32.0 minutes, i.e. the level of processing safety of the rubber compound in Example 7 of Table VII, which comprises 1.7 parts by weight sulfur, has actually become inferior to that of the control example. As
20 evidenced by Example 6 in Table VII, there is in fact a deterioration of the level of processing safety even at an addition of sulfur of more than 1.0 part by weight, as measured on the control compound (see Example 1, Table III). Rubber compounds which contain the crosslinking agents of the invention are suitable for the bonding or agglutination of natural or synthetic textile fibers (page 35, paragraph 2).

25

As described at the outset, there is, therefore, a pressing need for vulcanizable rubber compounds for the production of improved tire components, particularly with respect to industrial hygiene, processing safety of the rubber compound, and the mechanical and dynamic property profiles and aging behavior of vulcanized materials.

30

SUMMARY OF THE INVENTION


The object of the present invention is to provide vulcanizable rubber compounds, which exhibit a high capacity for the addition of sulfur to be varied while
5 maintaining high processing safety, for the production of improved tire components. The rubber compounds according to the invention release no nitrosamines during vulcanization which are carcinogenic to humans. The vulcanized materials resulting from the rubber compounds are free from undesirable odors of organosulfur compounds, and not only do the vulcanized materials exhibit no deterioration, or
10 exhibit only a slight deterioration in their technological properties during aging, but they are even improved before aging with respect to modulus and resistance to tear propagation, or their modulus remains virtually of the same standard while their resistance to tear propagation is improved without any deterioration in the standard of their other important technological properties, such as the loss factor $\tan \delta$ at 70°C
15 or the heat build-up.

In this connection, it should be mentioned that the modulus and the resistance to tear propagation are usually diametrically opposed to each other, i.e. vulcanized materials with a high modulus usually exhibit a low resistance to tear propagation, and vice
20 versa.

The object of the present invention has surprisingly been achieved by the vulcanization of a rubber compound based on diene rubbers which comprise a special crosslinking agent which provides C₆-bridges, in combination with a selected amount of sulfur,
25 and in the presence of vulcanization accelerators.

The present invention therefore relates to vulcanizable rubber compounds based on diene rubbers and customary additives, which are characterized in that the vulcanizing system contained in the compounds comprises
30

- a) 0.5 to 3.8 parts by weight of compound (I)



where R = (C₆H₅CH₂);

and X = 6,

b) 0.5 to 2 parts by weight sulfur

and

c) 0.5 to 3.0 parts by weight of vulcanization accelerators, wherein the parts by weight are given in each case with respect to the use of 100 parts by weight of rubber.

DETAILED DESCRIPTION OF THE INVENTION

The synthesis of chemical compound (I) of the crosslinking agent is described in principle in EP 0 432 405.

The rubber compound according to the present invention is produced in the manner known in the art by the customary mixing of the rubber components with known additives or supplementary materials, such as carbon black, plasticizers, antidegradants, zinc oxide, stearic acid or resins, as well as with the vulcanizing system, wherein the additives are used in customary amounts.

The following should be cited as diene rubbers in the present invention: natural rubber (NR), isoprene rubber (IR) and butadiene rubber (BR), as well as styrene-butadiene rubber (SBR) which can be produced either by the emulsion method or by the solution method. Equally good results are also obtained by using blends of these rubbers with each other.

With regard to diene rubber blends, a blend comprising 90 to 50 parts by weight, preferably 80 to 60 parts by weight, of NR, and 10 to 50 parts by weight, preferably 20 to 40 parts by weight, of BR, is particularly preferred.

5

The types of NR which are customarily used in the tire industry are suitable as NRs for the rubber compound according to the invention.

10

A BR which is particularly suitable for the rubber compound according to the invention is one which has a cis-1,4 content of 30 to 100 parts by weight, preferably of 90 to 100 parts by weight, per 100 parts by weight of rubber.

BR can be used in clear form or in oil-extended form. The use of clear BR is preferred.

15

Chemical compound (I) is used in amounts from 0.5 to 3.8 parts by weight, preferably in amounts from 0.5 to 3.5 parts by weight. The sulfur, which is customarily used in the rubber processing industry, or even insoluble sulfur, is suitable as the sulfur. The preferred amount of sulfur ranges from 0.5 to 2 parts by weight, more preferably from 0.5 to 1.5 parts by weight, with respect to 100 parts by weight of rubber used.

20

Known sulfur donors, for example, caprolactam disulphide, and admixtures thereof with sulfur, can also of course be used. The amount of sulfur donor, which is most favorable for the purpose of use, can easily be determined by preliminary tests.

25

Very different types of vulcanization accelerators can be used, and are subject to no restriction. Mercaptobenzthiazole (MBT), dibenzothiazyl disulphide (MBTS), sulphenamides based on MBT, such as benzothiazyl-2-cyclohexylsulphenamide (CBS), benzothiazyl-2-dicyclohexyl-sulphenamide (DCBS), benzothiazyl-2-tert.-butylsulphenamide (TBBS) and benzothiazyl-2-sulphenomorpholide (MBS) are

30

006750" 051900

preferably used. The vulcanization accelerators are used in amounts of 0.5 to 3.0 parts by weight, preferably 0.5 to 2.5 parts by weight, with respect to 100 parts by weight of rubber used.

5 A mixture of CBS and MBS is preferably used. Mixtures of other vulcanization accelerators can also be used, however, the optimum composition with respect to the type and amount thereof can easily be determined by experiment.

10 Vulcanization of the rubber compound according to the present invention is effected in the known manner at temperatures from about 120° to 220°C, preferably from 140° to 200°C.

15 The rubber compounds according to the present invention can be used for the production of rubber moldings, particularly tire components, and are most preferably used for the production of improved apices, sidewall strips and chafer strips, shoulder cushions, belt strips, sidewall inserts and tread slope bases, as well as for the treads of tires, particularly truck tires.

20 The invention is further illustrated but is not intended to be limited by the following examples in which all parts and percentages are by weight unless otherwise specified.

EXAMPLES

Details of the experimental methods used

- 5 The following test methods or test devices were used: Mooney viscosity: DIN 53 523, large rotor, 100°C, pre-heat time 1 minute, test duration 4 minutes. Mooney scorch: DIN 53 523, large rotor, 130°C, pre-heat time 1 minute. Rheometer: ASTM D 2084, Monsanto MDR 2000 E, 170°C. Tensile testing: DIN 53 405, dumb-bell. Hardness: DIN 53 505. Rebound resilience: DIN 53 512. Dynamic properties: DIN 10 53 533, Goodrich Flexometer, 100°C/25 minutes, pre-strain 1 MPa, stroke 4.45 mm. Viscoelastic properties: DIN 53 513/ISO 4664, Roelig Test, 10 Hz.

Examples 1 - 4

- 15 The test compounds listed in Table 1 were produced using an internal mixer Type GK 1,5 E manufactured by Werner & Pfleiderer, at a rotor speed of 40 rpm and at a chamber and blade temperature of 50°C (ram pressure 8 bar, degree of filling 65%). The quantities are given in parts by weight per 100 parts by weight rubber.

Table 1: Test formulations

Compound Number	Example 1 (Comparison 1)	Example 2	Example 3	Example 4 (Comparison 2)
NR ^{a)}	80	80	80	80
BR ^{b)}	20	20	20	20
Carbon black N234	40	40	40	40
Silica ^{c)}	8	8	8	8
Zinc oxide ^{d)}	10	10	10	10
Plasticizer ^{e)}	3	3	3	3
Tackifier ^{f)}	2	2	2	2
6PPD ^{g)}	1.8	1.8	1.8	1.8
TMQ ^{h)}	1.2	1.2	1.2	1.2
Stearic acid	0.75	0.75	0.75	0.75
Resorcinol formulation				
(66.6%) ⁱ⁾	1.2	1.2	1.2	1.2
HMT ^{j)}	0.6	0.6	0.6	0.6
CBS ^{k)}	0.7	0.7	0.7	0.7
MBTS ^{l)}	0.3	0.3	0.3	0.3
Sulfur	3	1	0.5	0.5
Cross-linking agent (I)	0	2	3	4

- a) TSR 5, Defo 700
- 5 b) Buna[®] CB 25 manufactured by Bayer AG, Leverkusen, Germany, cis-1,4 content: 96 % min., Mooney viscosity ML (1+4)100°C = 44
- c) Vulkasil[®] S manufactured by Bayer AG, Leverkusen, Germany, BET specific surface area: 155-195 m²/g, pH 5.4-7.0
- d) zinc oxide RS manufactured by Grillo Zinkoxide GmbH, Goslar, Germany
- 10 e) Enerthene[®] 1849/1 (aromatic mineral oil) manufactured by BP Oil Deutschland GmbH, Hamburg
- f) Koresin[®] powder manufactured by BASF AG, Mannheim, Germany
- g) Vulkanox[®] 4020/LG (N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine) manufactured by Bayer AG, Leverkusen, Germany
- 15 h) Vulkanox[®] HS/LG (polymerized 2,2,4-trimethyl-1,2-dihydroquinoline) manufactured by Bayer AG, Leverkusen, Germany
- i) Cohedur[®] RS manufactured by Bayer AG, Leverkusen, Germany

- j) Cohedur[®] H30 (hexamethylenetetramine, HMT) manufactured by Bayer AG, Leverkusen, Germany
- k) Vulkacit[®] CZ/C (benzothiazyl-2-cyclohexylsulphenamide, CBS) manufactured by Bayer AG, Leverkusen, Germany
- 5 l) Vulkacit[®] DM (dibenzothiazyl disulphide, MBTS) manufactured by Bayer AG, Leverkusen, Germany

The mixing sequence for the preparation of the compounds was selected as follows:

- 10 t = 0 sec addition of polymers
- t = 10 sec ram down
- t = 30 sec ram up, addition of carbon black and plasticizer, ram down
- t = 90 sec ram up, addition of silica, zinc oxide, tackifier, antidegradants, stearic acid and resorcinol, ram down
- 15 t = 210 sec sweep
- t = 240 sec dump.

On emptying the kneader, the temperatures of the mixed materials were within the range from 91 to 92°C.

- 20 HMT, as well as the vulcanization system consisting of sulfur, CBS, MBTS and crosslinking agent (I) were mixed in on a roll at a mixing temperature of about 60°C.

- 25 The rheological data which were determined on the finished rubber compounds are given in Table 2.

Table 2: Rheological data on test compounds

Compound number	Example 1 (Comparison 1)	Example 2	Example 3	Example 4 (Comparison 2)
ML (1+4) 100°C (MU)	64	69	67	73
Scorch time (120°)t ₅ (min)	15.3	23.3	28.0	29
Rheometer 150°C				
ts01 (min)	2.1	3.5	4.5	4.5
t95 (min)	10.1	9.0	12.9	13.4
Smin (dNm)	1.6	2.6	2.6	2.5
S'max (dNm)	17.9	19.5	18.6	19.8
Send, 30 min (dNm)	17.6	19.3	18.5	19.7
Rheometer 150°C				
ts01 (min)	0.5	0.7	0.9	0.9
t95 (min)	1.7	1.7	2.4	2.5
Smin (dNm)	1.4	2.4	2.3	2.3
S'max (dNm)	17.7	18.1	17.1	18.4
Send 30 min (dNm)	11.1	17.0	16.7	18.2

- 5 The rubber compounds according to the present invention were vulcanized at 150°C (vulcanization time: t95 + mold-related warming-up time). The test results on the vulcanized materials are given in Table 3.

Table 3: Properties of vulcanized test products

Vulcanized product number	Example 1 (Comparison 1)	Example 2	Example 3	Example 4 (Comparison 2)
Tensile strength (MPa)	21	24	22	20
Elongation at break (%)	440	452	423	382
Modulus 100 (MPa)	2.4	2.8	2.7	2.9
Modulus 300 (MPa)	12.4	14.2	13.9	14.7
Resistance to tear propagation (N/mm)	28	41	45	25
Hardness, 23°C (Shore A)	65	66	64	66
Hardness, 70°C (Shore A)	63	64	62	64
Rebound resilience, 23°C (%)	60	62	59	63
Rebound resilience, 70°C (%)	69	73	72	73
Goodrich flexometer:				
temperature increase (°C)	11	8	8	9
Flow (%)	5.3	0.9	0.6	1.0
Permanent set (%)	7.1	1.6	1.6	1.2
Roelig test:				
Tan δ , 0°C	0.113	0.104	0.104	0.108
Dyn. modulus E', 0°C (MPa)	6.38	6.76	6.63	7.09
Loss modulus E'', 0°C (MPa)	0.723	0.700	0.689	0.767
Tan δ , 70°C	0.043	0.035	0.041	0.050
Dyn. modulus E', 70°C (MPa)	5.91	6.23	5.95	6.28
Loss modulus E'', 70°C (MPa)	0.254	0.243	0.242	0.311

5 The examples teach that the rubber compounds according to the present invention exhibit a high level of processing safety, and result in vulcanized materials with an improved modulus and with an improved resistance to tear propagation at the same time, and in addition, exhibit low heat build-up and a low tan δ at 70°C.

Example 5

10

The procedure was the same as that used in Example 2 of Table 1, except that 2.0 parts by weight of sulfur were used instead of 1.0 parts by weight of sulfur and 1.0 part by weight of crosslinking agent (I) was used instead of 2.0 parts by weight of crosslinking agent (I).

15

The Mooney viscosity ML (1+4) 100°C of the compound obtained was 66 and the Mooney scorch time t_5 was determined as 21 minutes at 120°C.

5 After the corresponding vulcanization of the compound, the modulus 100 was 3.2 MPa; the resistance to tear propagation was 37 N/mm; and the temperature increase in the Goodrich Flexometer was determined to be 8°C. The Roelig test gave a tan δ of 0.035 at 70°C.

10 This example teaches that, compared with the control compound (see Example 1), rubber compounds according to the present invention even exhibit excellent processing safety when the addition of sulfur amounts to 2.0 parts by weight per 100 parts by weight of rubber.

Examples 6 and 7

15 The test compounds listed in Table 4 were produced using the internal mixer described in Examples 1 - 4 at a rotor speed of 40 rpm and at a chamber and blade temperature of 50°C (ram pressure 8 bar, degree of filling 65%). The quantities are given in parts by weight per 100 parts by weight rubber.

006T50" T505/650

Table 4: Test formulation

Compound number	Example 6	Example 7
	1 (Comparison)	2
NR ^{a)}	100	100
Carbon black N375	50	50
Zinc oxide ^{d)}	5	5
Plasticizer ^{e)}	3	3
6PPD ^{g)}	2	2
TMQ ^{h)}	1	1
Stearic acid	1	1
Microcrystalline wax ^{m)}	1	1
CBS ^{k)}	1	1
Sulfur	1.5	0.8
Crosslinking agent (I)	0	1.5

a) SMR 5, masticated

5 d), e), g), h), k) see the legend of Table 1

m) Antilux[®] 654 manufactured by Rhein Chemie Rheinau GmbH, Mannheim

The mixing sequence for the preparation of the compounds was selected as follows:

10 t = 0 sec addition of polymers
t = 10 sec ram down
t = 60 sec ram up, addition of carbon black, plasticizer, zinc oxide, stearic acid,
ram down
t = 120 sec ram up, addition of antidegradants and wax, ram down
15 t = 180 sec sweep
t = 240 sec dump

On emptying the kneader the temperatures of the mixed materials were within the range from 112° to 114°C.

- 5 The vulcanization system consisting of sulfur, accelerator and crosslinking agent (I) was mixed in on a roll at a mixing temperature of about 65°C.

The rheological data which were determined on the finished mixed rubber compounds are given in Table 5.

10 Table 5: Rheological data of the test compounds

Compound number	Example 6	Example 7
	1 (Comparison)	2
ML (1+4) 100°C (MU)	75	73
Scorch time (120°C) t ₅ (min)	21	26
Rheometer, 160°C		
ts01 (min)	1.6	2.1
t90 (min)	3.6	4.0
t95 (min)	4.0	4.9
S _{min} (dNm)	3.4	3.2
S' max (dNm)	16.8	17.8
Send, 30 min (dNm)	13.7	18.0
Reversion (%)	18	0
Rheometer, 180°C		
ts01 (min)	0.5	0.8
t90 (min)	1.1	1.5
t95 (min)	1.2	1.9
S _{min} (dNm)	3.3	2.9
S' max (dNm)	16.4	16.6
Send, 30 min (dNm)	10.8	15.7
Reversion (%)	34	5

The reversion was calculated as follows: $(S'_{\max} - S_{\text{end}}) / S'_{\max} \times 100\%$

5 The rubber compounds were vulcanized at 160°C (vulcanization time: $t_{95} + \text{mold-related warming-up time}$). The test results for the vulcanized materials are given in Table 6.

Table 6: Properties of vulcanized test products

Vulcanized product number	Example 6	Example 7
	1 (Comparison)	2
Tensile strength (MPa)	27	28
Elongation at break (%)	550	529
Modulus 100 (MPa)	2.1	2.8
Modul 300 (MPa)	11.5	13.4
Hardness, 23°C (Shore A)	67	68
Hardness, 70°C (Shore A)	61	62
Rebound resilience, 23°C (%)	43	40
Rebound resilience, 70°C (%)	56	52
Resistance to tear propagation (N/mm)	38	92
Abrasion (Emery 40) (mm ³)	161	112
Goodrich flexometer:		
Temperature increase (°C)	27	21
Flow (%)	8.7	2.3
Roelig test:		
tan δ , 0°C	0.215	0.222
Dyn. modulus E' , 0°C (MPa)	8.649	9.847
Loss modulus E'' , 0°C (MPa)	1.859	2.188
tan δ , 70°C	0.110	0.111
Dyn. modulus E' , 70°C (MPa)	5.229	5.896
Loss modulus E'' , 70°C (MPa)	0.577	0.656

5 The example teaches that the rubber compound according to the invention exhibits improved processing safety and results in a vulcanized material with improved abrasion resistance (the lower the abrasion, the higher the abrasion resistance) and an improved modulus together with improved resistance to tear propagation. In addition the vulcanized material according to the invention exhibits lower heat build-up.


10 Although the invention has been described in detail in the foregoing for the purpose of illustration, it is to be understood that such detail is solely for that purpose and that variations can be made therein by those skilled in the art without departing from the spirit and scope of the invention except as it may be limited by the claims.

0067507560

WHAT IS CLAIMED IS:

1. A vulcanizable rubber compound based on diene rubbers and customary additives, comprising a vulcanizing system contained in the compound comprising

- a) 0.5 to 3.8 parts by weight of compound (I)



wherein $R = (C_6H_5CH_2)$;

and $X = 6$;

- b) 0.5 to 2 parts by weight sulfur; and

- c) 0.5 to 3.0 parts by weight of at least one vulcanization accelerator wherein the parts by weight are given in each case with respect to 100 parts by weight of rubber.

2. A vulcanizable rubber compound according to Claim 1, wherein said compound (I) is present in an amount of 0.5 to 3.5 parts by weight.

3. A vulcanizable rubber compound according to Claim 1, wherein said sulfur is present in an amount of 0.5 to 1.5 parts by weight.


4. A vulcanizable rubber compound according to Claim 1, wherein said at least one vulcanization accelerator is present in an amount of 0.5 to 2.5 parts by weight.

5. A vulcanizable rubber compound according to Claim 1, wherein said at least one vulcanization accelerator is selected from the group consisting of mer-

captobenzthiazole (MBT), dibenzothiazyl disulphide (MBTS), sulphenamides based on MBT, such as benzothiazyl-2-cyclohexylsulphenamide (CBS), benzothiazyl-2-dicyclohexyl-sulphenamide (DCBS), benzothiazyl-2-tert.-butylsulphenamide (TBBS) and benzothiazyl-2-sulphenomorpholide (MBS) or mixtures thereof.

6. Rubber moldings comprising vulcanizable rubber compounds based on diene rubbers and customary additives, comprising a vulcanizing system contained in the compounds comprising

- a) 0.5 to 3.8 parts by weight of compound (I)



wherein $R = (C_6H_5CH_2)$;

and $X = 6$;

- b) 0.5 to 2 parts by weight sulfur; and

- c) 0.5 to 3.0 parts by weight of at least one vulcanization accelerator wherein the parts by weight are given in each case with respect to 100 parts by weight of rubber.

7. Rubber moldings according to Claim 6, wherein said compound (I) is present in an amount of 0.5 to 3.5 parts by weight.
8. Rubber moldings according to Claim 6, wherein said sulfur is present in an amount of 0.5 to 1.5 parts by weight.

9. Rubber moldings according to Claim 6, wherein said vulcanization accelerators are present in an amount of 0.5 to 2.5 parts by weight.
10. Rubber moldings according to Claim 6, wherein said at least one vulcanization accelerator is selected from the group consisting of mercaptobenzothiazole (MBT), dibenzothiazyl disulphide (MBTS), sulphenamides based on MBT, such as benzothiazyl-2-cyclohexylsulphenamide (CBS), benzothiazyl-2-dicyclohexyl-sulphenamide (DCBS), benzothiazyl-2-tert.-butylsulphenamide (TBBS) and benzothiazyl-2-sulphenomorpholide (MBS) or mixtures thereof.
11. Rubber moldings according to Claim 6, wherein said rubber molding is a molding for a tire component.

DIENE RUBBER COMPOUNDS FOR IMPROVED RUBBER MOLDINGS

ABSTRACT OF THE DISCLOSURE

This invention relates to vulcanizable diene rubber compounds with a high capacity for the addition of sulfur to be varied whilst processing safety is maintained, for the production of improved rubber moldings, particularly tire components.

006750" T 502/560

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name. I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

Diene rubber compounds for improved rubber moldings

the specification of which is attached hereto,

or was filed on _____ as

Application Serial No. _____

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims.

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, §1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s), the priority(ies) of which is/are to be claimed:

19925633.0
(Number)

Germany
(Country)

June 04, 1999
(Month/Day/Year Filed)

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose the material information as defined in Title 37, Code of Federal Regulations, §1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

(Application Serial No.)

(Filing Date)

(Status)

(patented, pending, abandoned)

(Application Serial No.)

(Filing Date)

(Status)

(patented, pending, abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

JOSEPH C. GIL, Patent Office Registration Number 26,602
ARON PREIS, Patent Office Registration Number 29,426
LYNDANNE M. WHALEN, Patent Office Registration Number 29,457
THOMAS W. ROY, Patent Office Registration Number 29,582
RICHARD E. L. HENDERSON, Patent Office Registration Number 31,619
GODFRIED R. AKORLI, Patent Office Registration Number 28,779
N. DENISE BROWN, Patent Office Registration Number 36,097
NOLAND J. CHEUNG, Patent Office Registration Number 39,138
CAROL MARMO, Patent Office Registration Number 39,761
DIDERICO VAN EYL, Patent Office Registration Number 38,641

all of Bayer Corporation, Pittsburgh, Pennsylvania 15205-9741

Send Correspondence To: Patent Department Bayer Corporation 100 Bayer Road Pittsburgh, Pennsylvania 15205-9741	Direct Telephone Calls To: (412) 777-2349
---	---

FULL NAME OF SOLE OR FIRST INVENTOR Winfried JESKE	INVENTOR'S SIGNATURE <i>Winfried Jeske</i>	DATE 2000/04/27
RESIDENCE 51399 Burscheid, Germany	CITIZENSHIP German	
POST OFFICE ADDRESS Irlerhof 32, 51399 Burscheid, Germany		
FULL NAME OF SECOND INVENTOR Hartmuth BUDING	INVENTOR'S SIGNATURE <i>Hartmuth Buding</i>	DATE 2000/05/03
RESIDENCE 52445 Titz, Germany	CITIZENSHIP German	
POST OFFICE ADDRESS Lönsstr. 23, 52445 Titz, Germany		
FULL NAME OF THIRD INVENTOR Hermann-Josef WEIDENHAUPT	INVENTOR'S SIGNATURE <i>Hermann-Josef Weidenhaupt</i>	DATE 2000/04/27
RESIDENCE 50259 Pulheim, Germany	CITIZENSHIP German	
POST OFFICE ADDRESS Kantstr. 6 a, 50259 Pulheim, Germany		

005750" T 305 330